


A6063-T5 平角

〈比重=2.69〉



●在庫・△取寄


a	b	長さ mm	1本重量 kg	在庫
2.0	10.0	4,000	0.22	△
2.0	15.0		0.33	●
2.0	20.0		0.43	●
2.0	25.0		0.54	●
2.0	30.0		0.65	●
2.0	40.0		0.87	△
2.0	50.0		1.08	△
3.0	10.0		0.33	●
3.0	12.0		0.39	△
3.0	15.0		0.49	●
3.0	20.0		0.65	●
3.0	25.0		0.81	●
3.0	30.0		0.98	●
3.0	35.0		1.14	△
3.0	40.0		1.30	●
3.0	50.0		1.63	●
3.0	60.0		1.95	△
3.0	70.0		2.28	△
4.0	10.0		0.43	●
4.0	12.0		0.52	●
4.0	15.0		0.65	●
4.0	20.0		0.87	●
4.0	25.0		1.09	●
4.0	30.0		1.31	●
4.0	40.0		1.74	●
4.0	50.0		2.17	●
4.0	60.0		2.60	△
4.0	70.0		3.04	△
5.0	10.0		0.55	●
5.0	12.0		0.62	●
5.0	15.0		0.81	●
5.0	20.0		1.08	●
5.0	25.0		1.36	●
5.0	30.0		1.63	●
5.0	35.0		1.90	△
5.0	40.0		2.17	●
5.0	50.0		2.72	●
5.0	60.0		3.25	●
5.0	70.0		3.80	●
5.0	100.0		5.42	●

*●印は在庫がございます。△印は取寄になります。
*1本重量は、実際の販売重量と若干異なる場合があります。

A6063-T5 平角

<比重=2.69>

●在庫・△取寄




a	b	長さ mm	1本重量 kg	在庫
6.0	9.0	4,000	0.59	●
6.0	10.0		0.65	●
6.0	12.0		0.78	●
6.0	15.0		0.98	●
6.0	20.0		1.30	●
6.0	25.0		1.65	●
6.0	30.0		1.95	●
6.0	35.0		2.28	●
6.0	40.0		2.60	●
6.0	50.0		3.25	●
6.0	60.0		3.90	●
6.0	75.0		4.90	●
6.0	100.0		6.50	●
6.0	160.0		10.41	△
8.0	15.0		1.30	●
8.0	20.0		1.74	●
8.0	25.0		2.20	●
8.0	30.0		2.60	●
8.0	32.0		2.78	●
8.0	35.0		3.04	●
8.0	40.0		3.47	●
8.0	50.0		4.34	●
8.0	60.0		5.20	●
8.0	75.0		6.50	●
8.0	100.0		8.67	△
9.0	20.0		1.95	△
9.0	30.0		2.93	△
9.0	40.0		3.90	△
9.0	50.0		4.88	△
9.0	60.0		5.84	△
9.0	75.0		7.29	△
9.0	100.0		9.72	△

*●印は在庫がございます。△印は取寄になります。
*1本重量は、実際の販売重量と若干異なる場合があります。



A6063-T5 平角

〈比重=2.69〉



●在庫・△取寄


a	b	長さ mm	1本重量 kg	在庫
10.0	15.0	4,000	1.63	●
10.0	20.0		2.17	●
10.0	25.0		2.71	●
10.0	30.0		3.27	●
10.0	35.0		3.80	●
10.0	40.0		4.34	●
10.0	45.0		4.88	●
10.0	50.0		5.44	●
10.0	60.0		6.50	●
10.0	64.0		6.94	△
10.0	70.0		7.59	●
10.0	75.0		8.16	●
10.0	80.0		8.67	●
10.0	100.0		10.84	●
10.0	120.0		12.96	△
10.0	125.0		13.50	●
10.0	150.0		16.28	●
12.0	15.0		1.95	●
12.0	20.0		2.60	●
12.0	25.0		3.26	●
12.0	30.0		3.90	●
12.0	40.0		5.24	●
12.0	50.0		6.50	●
12.0	60.0		7.81	△
12.0	75.0		9.72	●
12.0	100.0		12.96	●
12.0	120.0		15.55	●
13.0	25.0		3.54	●
13.0	40.0		5.64	●
15.0	20.0		3.25	●
15.0	25.0		4.08	●
15.0	30.0		4.92	●
15.0	40.0		6.53	●
15.0	50.0		8.16	●
15.0	60.0		9.76	●
15.0	75.0		12.20	●
15.0	100.0		16.26	●
15.0	150.0		24.39	△
15.0	200.0	2,500	20.33	△
20.0	25.0	4,000	5.44	●
20.0	30.0		6.50	●
20.0	35.0		7.60	●

*●印は在庫がございます。△印は取寄になります。
*1本重量は、実際の販売重量と若干異なる場合があります。

A6063-T5 平角

<比重=2.69>

●在庫・△取寄



a	b	長さ mm	1本重量 kg	在庫
20.0	40.0	4,000	8.67	●
20.0	50.0		10.84	●
20.0	60.0		13.01	●
20.0	70.0		15.21	●
20.0	80.0		17.28	●
20.0	100.0	2,000	10.88	●
20.0	150.0	4,000	20.33	△
20.0	200.0	2,500	27.10	△
25.0	30.0	4,000	8.12	●
25.0	35.0		9.52	●
25.0	40.0		10.88	●
25.0	50.0		13.60	●
25.0	60.0		16.26	●
25.0	80.0		21.68	●
25.0	100.0		16.94	△
25.0	150.0		25.41	△
25.0	200.0		33.88	△
30.0	40.0		13.00	●
30.0	50.0		16.30	●
30.0	60.0		19.60	●
30.0	65.0		21.20	●
30.0	75.0		24.40	●
30.0	100.0		32.44	●
30.0	150.0	2,500	30.49	△
30.0	200.0		40.65	△
35.0	40.0	4,000	15.24	●
35.0	50.0		18.97	●
35.0	60.0		22.76	●
35.0	85.0		32.25	△
35.0	100.0	2,500	23.72	△
40.0	50.0	4,000	21.68	●
40.0	60.0		26.12	●
40.0	75.0		32.52	●
40.0	100.0		43.20	●
50.0	100.0	2,500	33.90	△
76.0	100.0		51.49	△

*●印は在庫がございます。△印は取寄になります。
*1本重量は、実際の販売重量と若干異なる場合があります。

A6063 (熱処理系)

Al-Mg-Si系合金。代表的な押出合金。6061より強度は低いが押出性に優れ、複雑な断面形状の形材が得られ、耐食性、表面処理性も良好である。

用途例:

建築・車輛・家具・家電製品・サッシ



化学成分表 (%)

Al	Cu	Si	Fe	Mn	Mg	Zn	Cr	Ti	Zr	その他
残部	0.10以下	0.2~0.6	0.35以下	0.10以下	0.45~0.9	0.10以下	0.10以下	0.10以下	—	—

機械的性質

調質	引張強さ (N/mm ²)	耐力 (N/mm ²)	伸び (%)
T5	185	145	12

*データは参考値であり保証値ではございません。